

Phone: (517) 295-4196 Fax: (517) 295-4918

Technical Data Sheet

LCA® N6-40GMHSL Black

Nylon 6 Glass Mineral, Heat Stabilized, Lubricated

Typical Compound Prope	erties Value / Measure	Test Methods	
Physical Properties	English Units		
i nysicar i roperties	g		
Density	1.46 g/cm	n3 ASTM D-792	
Ash Content	40 %	ASTM D-5630	
Mechanical Properties			
Izod Impact	0.90 ft-lb/	in ASTM D-256	
Tensile Strength	17,000 psi	ASTM D-638	
Flexural Modulus	1,000,000 psi	ASTM D-790	
Thermal Properties			
Melt Point	220 Deg.	. C ASTM D-789-92e1	
All tests are performed on dry as molded ASTM (ISO) test bars.			
General Product Type Information			

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Uniplas, Inc. disclaims any liability for loss or damage incurred in connection with the use of this product.



Phone: (517) 295-4196 Fax: (517) 295-4918

Technical Data Sheet

LCA® N6-40GMHSL Black

Nylon 6 Glass Mineral, Heat Stabilized, Lubricated

Process Variable	Typical Processing Conditions Description	
Temperatures		F
Barrel	Rear Center Front Nozzle Mold	460 - 540 480 - 560 480 - 560 470 - 550 150 - 200
Drying Type Temperature Time Max. % Moisture		

Special Requirements

Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.